



台湾化学纤维股份有限公司

TAIRILAC® ABS 树脂

项目 Property	单位 Unit	试验方法 Test Method	试验条件 Test Condition	押出级
				AG10NP
抗张强度 Tensile Strength	kg/cm ² (MPa)	ASTM D-638	23 °C	450 (44)
弯曲强度 Flexural Strength	kg/cm ² (MPa)	ASTM D-790	23 °C	740 (73)
弯曲模数 Flexural Modulus	kg/cm ² (MPa)	ASTM D-790	23 °C	23000 (2260)
洛氏硬度 Rockwell Hardness	R-scale	ASTM D-785	23 °C	R-102
Izod 冲击强度 Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23 °C 1/4"	44 (431)
卫氏软化点 Vicat Softening Point	°C	ASTM D-1525	1Kg load	101
热变形温度 Heat Deflection Temperature	°C	ASTM D-648	Unannealed 18.6 kg/cm ² (1/4"bar)	88
			Annealed (80°C×8hr)	98
熔融指数 Melt Flow Index	g/10 min	ASTM D-1238	200°C×5kg (49N)	-
			220°C×10kg (98N)	6
收缩率 Molding Shrinkage	%	ASTM D-955	3.2mm	0.4~0.7
比重 Specific Gravity		ASTM D-792	23°C/23°C	1.04
燃烧性 Flammability		UL-94	File No. E162823	1.6-1.76mm HB All Color
特性 Characteristics	押出成型用 超高耐冲击性 高刚性			

以上数值系参考 ASTM、ISO 试验方法所测得，仅供选择用途品级之参考。

台湾化学纤维股份有限公司-塑料部

电话: 02-27122211 / 传真: 02-27131649

地址: 台北市松山区敦化北路 201 号

网址: <https://www.fcfc-plastics.com>

